

ProJet® MJP 2500 IC

Tool-less 100% wax investment casting pattern production with industrial Multijet Printing



ProJet MJP 2500 IC

Printing Mode	HD - High Definition
Net Build Volume (xyz)*	11.6 x 8.3 x 5.6 in (295 x 211 x 142 mm)
Resolution (xyz)	600 x 600 x 600 DPI; 42 µm layers
Accuracy (typical)**	±0.004 in/in (±0.1016 mm/25.4 mm) of part dimension across printer population ±0.002 in/in (±0.0508 mm/25.4 mm) of part dimension typical for any single printer
Volumetric Print Speed	1 Lane 12.5 in ³ /hour (205 cm ³ /hour) 2 Lanes 12.1 in ³ /hour (199 cm ³ /hour) 3 Lanes 11.6 in ³ /hour (189 cm ³ /hour)
Build Material	Visijet® M2 ICast
Support Material	Visijet® IC SUW
Material Packaging	
Build Material	In clean 2.87 lbs (1.3 kg) bottles (printer holds up to 2 with auto-switching)
Support Material	In clean 2.87 lbs (1.3 kg) bottles (printer holds up to 2 with auto-switching)
Electrical	100-127 VAC, 50/60 Hz, single-phase, 15A 200-240 VAC, 50 Hz, single-phase, 10A Single C14 receptacle
Dimensions (WxDxH)	
3D Printer Crated	55 x 36.5 x 51.7 in (1397 x 927 x 1314 mm)
3D Printer Uncrated	44.1 x 29.1 x 42.1 in (1120 x 740 x 1070 mm)
Weight	
3D Printer Crated	716 lb (325 kg)
3D Printer Uncrated	465 lb (211 kg)
3D Sprint™ Software	Easy build job set-up, submission and job queue management; Automatic part placement and build optimization tools; Part stacking and nesting capability; Extensive part editing tools; Automatic support generation; Job statistics reporting tools
E-mail Notice Capability	Yes
Internal Hard Drive Capacity	500 Gb minimum
Connectivity	Network ready with 10/100/1000 base ethernet interface USB port
Client Operating System	Windows® 7, Windows 8 or Windows 8.1 (Service Pack)
Input Data File Formats Supported	STL, CTL, OBJ, PLY, ZPR, ZBD, AMF, WRL, 3DS, FBX, IGES, IGS, STEP, STP, MJPDDD
Operating Temperature Range	Optimal 64-75 °F (18-24 °C), not to exceed 82 °F (28 °C)
Operating Humidity	30-70 % relative humidity
Noise	< 65 dBa estimated (at medium fan setting)
Certifications	CE, UL, EAC, KCC and FCC

* Maximum part size is dependent on geometry, among other factors.

** Across printer variation can be reduced to equal single printer variation via user calibration.

Accuracy may vary depending on build parameters, part geometry and size, part orientation, and post-processing.

VisiJet® M2 ICast

High performance RealWax™ material for direct metal casting



Properties	Condition	VisiJet M2 ICast	VisiJet M2 IC SUW
Composition		100% Wax	Wax Support Material
Color		Green	White
Bottle Quantity		1.3 kg	1.3 kg
Density @ 80 °C (liquid)	ASTM D3505	0.80 g/cm ³	0.87 g/cm ³
Melting Point		61-66 °C	55-65 °C
Softening Point		40-48 °C	N/A
Volumetric Shrinkage, from 40 °C to RT		2 %	N/A
Linear Shrinkage, from 40 °C to RT		0.70 %	N/A
Needle Penetration Hardness	ASTM D1321	12	N/A
Ash Content	ASTM 2584	< 0.05 %	N/A
Printer Compatibility		Projet MJP 2500 IC	Projet MJP 2500 IC
Description		High resolution, durable casting wax An unfilled paraffin based wax with added resins	Non-toxic wax support material with easy break-away structure and dissolvable hands-free removal



middle east
3D PRINTING THE FUTURE

3D SYSTEMS®
DISTRIBUTOR | Middle East & North Africa

U.A.E Office : 3204, Prism Tower, Business Bay, P.O. Box 28820, Dubai, U.A.E.

K.S.A Office : Al Saif Tower, 6th Floor, King Abdullah Street, Near Intersection with Olaya Street, Riyadh, K.S.A.

Tel : +971.4.443.3853 ; Fax : +971.4.443.3938 ; Email : info@3d-me.com ; Website: www.3d-me.com